

Entwicklungs- und Prüflabor Holztechnologie GmbH · Zellescher Weg 24 · 01217 Dresden · Germany

Centexbel  
Kristina de Temmerman  
Technologiepark 70  
B - 9052 Gent-Zwijnaarde

Belgium

E-Mail: [kdt@centexbel.be](mailto:kdt@centexbel.be)

Bru/50

Dresden, 18 January 2023

## Test Report no. 2523006

**Client:** Centexbel  
Technologiepark 70  
B - 9052 Gent-Zwijnaarde  
Belgium

**Order:** Testing of floor covering regarding:  
○ formaldehyde release based on test chamber method EN 717-1

**T2224943**

**Contractor:** Entwicklungs- und Prüflabor Holztechnologie GmbH (EPH)  
Laboratory Chemical Testing  
Zellescher Weg 24  
01217 Dresden

**Engineer in charge:** Dipl.-Ing. (FH) S. Hahn



Dipl.-Ing. Martina Broege  
Head of Laboratory Chemical Testing

The test report contains 2 pages. Any duplication, even in part, requires written permission of EPH. These test results are exclusively related to the tested material.



### 1 Assignment

The laboratory chemical testing of the EPH was instructed to determine the formaldehyde release of floor covering based on test chamber method EN 717-1.

### 2 Sample material

Sample delivery EPH: 03/01/2023, airtight wrapped

Sample	Description	Size Test pieces (TP)	Thickness [mm]
1	Floor covering T2224943	5 TP 1000 mm x 190 mm	4

The test material was used up respectively is stored for 3 months.

### 3 Test chamber method EN 717-1

Method: EN 717-1:2005-01; Wood-based panels - Determination of formaldehyde release - Part 1: Formaldehyde emission by the chamber method

The determination of the formaldehyde release was carried out according to the chamber method EN 717-1:2005 (Testing "back to back") under following test conditions:


Sample 1			
Test pieces (TP):	4 TP à 200 x 280 [mm]	Temperature (T):	23°C ± 0.5 K
Test chamber:	KT-39 (0.225 m <sup>3</sup> )	Air exchange ratio:	1.0 ± 0.05/ h
Test period:	05/01/2023 - 11/01/2023	Loading ratio:	1.0 ± 0.02 m <sup>2</sup> /m <sup>3</sup>
Start tests:	06/01/2023	Rel. air humidity (RH):	45 ± 3 %
Edge sealing:	Full	Parameter recording:	T; RH

Limit of Detection (LOD) of test method: 0.008 ppm HCHO

### 4 Test results test chamber method EN 717-1 and Evaluation<sup>1</sup>

Sample	Formaldehyde release EN 717-1			*	German Prohibition of Chemical Ordinance <sup>2</sup> Quality fulfilled	
	Unit	Measured value	measured value multiplied by factor 2		Yes	No
1	ppm	< LOD	< LOD	I (144)	<input checked="" type="checkbox"/>	<input type="checkbox"/>
	µg / m <sup>3</sup>	< LOD	< LOD			

- \* Cancellation criteria EN 717-1:
- I lower detection limit over a testing time of 4 days
  - II linear regression function from the test results of 4 consecutive days does not increase by more than 2 µg/m<sup>3</sup>
  - III the decline of the calculated concentration curve is equal or lower than 5% over the testing time of 4 days (within 28 days)
  - IV completely regression curve (max. 28 days)

  
Dipl.-Ing. (FH) S. Hahn  
Engineer in charge

<sup>1</sup>Statements on conformity assessment/classification were made on the basis of the measurement results obtained. Measurement uncertainties are not included in the assessment (ILAC G8 03/2009 " Guidelines on the Reporting of Compliance with Specification" Section 2.7).

<sup>2</sup> German Chemical Prohibition Ordinance appendix 1 of §3 dated 2017-01-20 in connection with "Bekanntmachung analytischer Verfahren" published on 26 November 2018, BAnz AT 26.11.2018 B2

- Formaldehyde limit value acc. to German Prohibition of Chemical Ordinance 0.1 ppm (124 µg/m<sup>3</sup>)

- Test results according to DIN EN 717-1 are multiplied by the factor 2

- according to UBA correspond to 0,1 ppm ≙ 124 µg/m<sup>3</sup>; <https://www.umweltbundesamt.de/themen/wirtschaftskonsum/produkte/bauprodukte/studien-zur-messung-bewertung-von-schadstoffen/formaldehydmissionen-pruefbedingungen-fuer>, Status 2019-06-12